



**Third United Nations
International Conference
on the Peaceful Uses
of Atomic Energy**

A/CONF.28/A/554
ITALY

February 1964

Submitted in:
ENGLISH and FRENCH

Confidential until official release during Conference

Abstract

UO₂ FUEL ELEMENTS SHAPED AS SMALL SPHERES

A. Bassi, E. Brutto, R. Di Pietro, G. Perona and R. Sesini
C.I.S.E., Milano (Italia)

In connection with a type of reactor design under investigation at the Technological Laboratory of CISE, a research programme on the manufacture and the characteristics of small, coated UO₂-spheres (1 ÷ 4 mm in diameter) has been carried out during the last two years. Those fuel particles might be generally in any reactor design involving the use of fuel as fixed or fluidized bed.

The following manufacture procedure has been developed for the spheres: adding to the UO₂ powder a solution with binding agents (the solvent can be water) a paste is obtained which is grinded in a ball mill. Part of the solvent having been evaporated, a bar is manufactured by extrusion. This is subdivided into small cylinders which are placed in vibrating small cells (one cylinder in each cell) for 3 to 4 minutes. By knocking against the walls of the cavity the particles assume a spherical shape. A standard procedure is used to sinter these spheres.

Up to now only a Ni-Cr coating has been studied. First a 5μ thick Ni-layer is deposited chemically on the UO₂ surface, to which it adheres very well. A second 10 μ Ni-layer is then deposited by means of an electrolytic process. Eventually a third Cr-layer, 10 μ thick, is electrolytically deposited. After a successive 850°C annealing for 5 hours, a Ni-Cr alloy is obtained.

In order to study the strength to thermal stresses, like those present during the reactor operation, a testing procedure has been developed in which the spheres undergo a thermal shock. They are first heated up to a temperature T₀, then quickly cooled down with a blast of steam and water at a lower temperature T₀ < T₀. For the detection of any possible damage, the spheres are examined by using proper detectors.

The presence of small cracks indicates that the critical temperature difference has been exceeded. By knowing the critical temperature difference, many interesting physical properties of the material can be derived. For these tests uncoated UO_2 spheres are used.

The coating has the essential purpose of preventing the oxidation of UO_2 into superior oxide compounds by the hot water and the suitability of the Ni-Cr layer to protect UO_2 was checked by tests in autoclave.

A first series of tests yielded very positive results: no surface damage was detected. A new set of tests, with a much longer exposition time, are currently under way.

An in-pile technique is now being studied for the measurement of fission gas release from the spheres.